

Solu-Cell P2000 Series

Chemically Cross Linked Polyolefin Foam

Physical Properties Description

Physical Properties	Result	Test Method	Tolerances
Hardness, Duro A/00	10/48	ASTM D2240	+/-10%
Density	2.0 lb/cu ft	ASTM D3575	+/-1 lb/cu ft
Compression Strength	55-65 kPa	ASTM D3575-08 (D)	+/-10%
Tensile Strength	48 psi	ASTM D3575	+/-10%
Elongation	245 %	ASTM D3575	+/-10%
Thermal Stability	2%	ASTM D3575	+/-0.01 lbs/sq ft
FMVSS302	Passed		

Standard Colors: White, Light Gray, Charcoal, Black – other colors available on request.

Dimensional Specifications – Minimum Useable

Width	Length	Thickness
48	96	4
48	72	4

Three-Sixty Solutions, Inc. offers this information as a technical service. These results are for reference purposes and are intended to be for a guideline of performance only, as results may vary. The information is believed to be reliable to the extent to our knowledge and ability, using standardized methods and procedures. All users should rely on their own tests. Three-Sixty Solutions, Inc. claims no responsibility for the results of this information. Since Three-Sixty Solutions, Inc. cannot control the end use or environment of this product, it does not guarantee that the user will obtain the same results as published in this document. Data is subject to change without notice.

Revised: April 2015